

Revision Date: 4/26/2013 5P09B Version 5



Microporous Polyethylene Film

SOLUPOR® membranes are highly porous with high gas, air and liquid permeability. Combined with a controlled pore size, this makes SOLUPOR® membranes suitable for a range of filtration applications. Made from Ultra High Molecular Weight Polyethylene, using a unique patented proprietary manufacturing technology

Features

Thin

Highly porous

Chemical Composition

Polymer

(Ultra) High Molecular Weight Polyethylene

General Properties

	Typical Value	Unit	Test Method
Total Weight per Surface Area	5	g/m²	MV 001
Thickness	38	μm	MV 002
Porosity	86	%	MV 001
Air Permeability, Gurley number	2	s/50 ml	MV 006
Mean Flow Pore Size	0.9	μm	MV 003

Additional Properties

	Typical Value	Unit	Test Method
Tensile Strength @ Machine Direction	8	MPa	MV 010 / ASTM D882-12
Elongation at Break @ Machine Direction	35	%	MV 010 / ASTM D882-12
Dimensional Changes @ 80 ℃			
- Machine Direction	<1	%	MV 009
- Transverse Direction	<1	%	MV 009

Lydall Filtration/Separation SAS (Europe, Middle East & Africa Sales): Saint Rivalain, France, +33 (0) 2 97 28 5300

Lydall Solutech B.V.: Eisterweg 4, 6422 PN Heerlen, The Netherlands, +31 (0) 45 751 5212

E-mail: info_solupor@lydall.com -or- info@lydall.com **Web:** www.solupor.com - or - www.lydallfiltration.com

All data and statements concerning these products may be considered as being indicative of representative properties and characteristics obtainable. Since industry practices vary, we make no warranty, express or implied, concerning their use, nor do we accept responsibility. SOLUPOR® is a trademark of Lydall Solutech BV.

